



10414163
AS

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of Schmidt	Attorney Docket # 1933.BDM
Serial No. 09/882,241	Examiner: T. Ribar
Filing Date: June 15, 2001	Group Art Unit: 1711
Title: Reactive Hot Melt Adhesive	Date of this response: April 4, 2003

Assistant Commissioner of Patents
Washington, DC 20231

APR 14 2003

RESPONSE

Dear Sir,

This is in response to paper number 2 mailed November 6, 2002. The time to respond has been extended to April 6, 2003 by the Petition for Extension of Time filed herewith. Claims 1 – 13 are pending in the application. Claims 1 – 13 are rejected.

Kindly enter the following amendments to the specification and claims. Marked-up versions of the specification and claims are included as Appendix 1 with this response.

AMENDMENTS

IN THE SPECIFICATION

Please replace the Table on Page 14 with the following new Table:

Table

Material	Sample A	Sample B	Sample C
PPG 2025	20	39	30
PPG 4025	20	---	---
DYNACOL 7360	20	---	12.5
DYNACOL 7380	---	---	7.5
RUCO S 105-10	---	18	---
ELVACITE 2967	---	---	21.5
ELVACITE 2901	---	---	16.5
ELVACITE 2016	28	28	---
MONDUR	12	15	12.0
DMDEE	0.2	0.2	0.2
Viscosity @ 275°F	8,000	20,000	10,000
1 hour Tensile psi	33	500	1200
30 sec. Cantilever Test	No Substrate Failure	Partial Substrate Failure	Total Substrate Failure
Open Time min.	4	4	4

PPG 2025 (a polyether polyol - available from Bayer)
PPG 4025 (a polyether polyol - available from Bayer)
DYNACOL 7360 (a hexanediol adipate - available from Creanova)
DYNACOL 7380 (a polyester polyol - available from Creanova)

21